


Material: CuNi 90/10
CuNi 70/30



Outside diameter of pipe			Schedule 5S				Schedule 10S			
			Wall thickness		Theoretical weight		Wall thickness		Theoretical weight	
ØD			actual inch	actual mm	Lb/Ft	Kg/m	actual inch	actual mm	Lb/Ft	Kg/m
nominal inch	actual inch	actual mm								
0.125	0.405	10.29	-	-	-	-	0.049	1.24	0.19	0.28
0.25	0.54	13.72	-	-	-	-	0.065	1.65	0.33	0.49
0.38	0.675	17.15	-	-	-	-	0.065	1.65	0.42	0.63
0.5	0.84	21.34	0.065	1.65	0.54	0.8	0.083	2.11	0.67	1
0.75	1.05	26.67	0.065	1.65	0.69	1.03	0.083	2.11	0.86	1.28
1	1.315	33.4	0.065	1.65	0.87	1.3	0.109	2.77	1.4	2.09
1.25	1.66	42.16	0.065	1.65	1.11	1.65	0.109	2.77	1.81	2.7
1.5	1.9	48.27	0.065	1.65	1.28	1.91	0.109	2.77	2.09	3.11
2	2.375	60.32	0.065	1.65	1.61	2.4	0.109	2.77	2.64	3.93
2.5	2.875	73.03	0.083	2.11	2.48	3.69	0.12	3.05	3.53	5.26
3	3.5	88.9	0.083	2.11	3.03	4.51	0.12	3.05	4.33	6.45
3.5	4	101.6	0.083	2.11	3.48	5.18	0.12	3.05	4.97	7.4
4	4.5	114.3	0.083	2.11	3.92	5.84	0.12	3.05	5.61	8.36
5	5.563	141.3	0.109	2.77	6.36	9.47	0.134	3.4	7.77	11.57
6	6.625	168.3	0.109	2.77	7.6	11.32	0.134	3.4	9.29	13.84
8	8.625	219.1	0.109	2.77	9.93	14.79	0.148	3.76	13.4	19.96
10	10.75	273.05	0.134	3.4	15.19	22.63	0.165	4.19	18.65	27.78
12	12.75	323.9	0.156	3.96	20.98	31.25	0.18	4.57	24.17	36

Outside diameter of pipe			Schedule 40S				Schedule 80S			
			Wall thickness		Theoretical weight		Wall thickness		Theoretical weight	
ØD			actual inch	actual mm	Lb/Ft	Kg/m	actual inch	actual mm	Lb/Ft	Kg/m
nominal inch	actual inch	actual mm								
0.125	0.405	10.29	0.068	1.73	0.24	0.37	0.095	2.41	0.31	0.47
0.25	0.54	13.72	0.088	2.24	0.42	0.63	0.119	3.02	0.54	0.8
0.38	0.675	17.15	0.091	2.31	0.57	0.84	0.126	3.2	0.74	1.1
0.5	0.84	21.34	0.109	2.77	0.85	1.27	0.147	3.73	1.09	1.62
0.75	1.05	26.67	0.113	2.87	1.13	1.69	0.154	3.91	1.47	2.2
1	1.315	33.4	0.133	3.38	1.68	2.5	0.179	4.55	2.17	3.24
1.25	1.66	42.16	0.14	3.56	2.27	3.39	0.191	4.85	3	4.47
1.5	1.9	48.27	0.145	3.68	2.72	4.05	0.2	5.08	3.63	5.41
2	2.375	60.32	0.154	3.91	3.65	5.44	0.218	5.54	5.02	7.48
2.5	2.875	73.03	0.203	5.16	5.79	8.63	0.276	7.01	7.66	11.41
3	3.5	88.9	0.216	5.49	7.58	11.29	0.3	7.62	10.25	15.27
3.5	4	101.6	0.226	5.74	9.11	13.57	0.318	8.08	12.51	18.63
4	4.5	114.3	0.237	6.02	10.79	16.07	0.337	8.56	14.98	22.32
5	5.563	141.3	0.258	6.55	14.62	21.77	0.375	9.53	20.78	30.97
6	6.625	168.3	0.28	7.11	18.97	28.26	0.432	10.97	28.57	42.56
8	8.625	219.1	0.322	8.18	28.55	42.55	0.5	12.7	43.39	64.64
10	10.75	273.05	0.365	9.27	40.48	60.31	0.5	12.7	54.74	96.01
12	12.75	323.9	0.375	9.53	49.56	73.88	0.5	12.7	65.42	132.08

